

Extra-Firm Grade Silicone Foam Name 88-NS160 Code

1. DIMENSIONS AND APPEARANCE

Thickness	in
Length	ft
Width, for $\frac{1}{16}$ to $\frac{3}{32}$ in thickness	in
Width, for $1/_8$ to $1/_2$ in thickness	in
Surface finishing	
Color	

 $\frac{1}{16} - \frac{1}{2}$ 16.4 - 65.6, depending on thickness 34 18 Smooth Grey, Black, *White, *Red *Subject to MOQ

2. **PHYSICAL PROPERTIES**

Compression deflection (25%) Density Compression set (22h, 100°C) Tensile strength Elongation Water absorption Flammability Low temperature flexibility	psi (kPa) pcf (kg/m ³) % psi (kPa) % - °C (°F)	29 (200) 34 (550) < 1 87 (600) 90 3 V-0 rating -55 (-67)	ASTM D1056 ASTM D1056 ASTM D1056 ASTM D412 ASTM D412 ASTM D1056 UL-94 ASTM D1056
Working temperature range	°C (°F)	-55 to 200 (-67 to 392)	

INDUSTRY STANDARDS 3.

FDA regulation 21 CFR 77.2600 UL-94 V-0

Rubber articles intended for repeated use \geq 0.8mm thickness

TOLERANCES 4.

TARGET THICKNESS, in (mm)	MINIMUM, mm	MAXIMUM, mm
1/32 (0.8)	0.698	1.181
1/16 (1.6)	1.092	2.108
3/32 (2.4)	1.892	2.908
1/8 (3.2)	2.565	3.835
3/16 (4.8)	4.165	5.435
1/4 (6.4)	5.638	7.162
3/8 (9.5)	8.357	10.643
1/2 (12.7)	11.430	13.970

Length tolerance	+free / -0
Width tolerance	+free / -0

GCP Elastomeric Inc. cannot foresee all circumstances under which this information and our products in conjunction with other manufactures products may be used. Physical properties are typical values obtained from sample testing at Akron laboratories or GCP Approved Supplier[™] laboratories. Actual production values may vary. It is the users' responsibility to ensure the products are appropriate for their application. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. If you have any questions in this regard please contact our technical director George Qu (george@gcpindustrial.com).