

SPECIFICATION SHEET

Oct-2022 GCP Industrial Products

Name Medium Grade Silicone Foam

Code 88-NS120

1. DIMENSIONS AND APPEARANCE

Thickness in $\frac{1}{32} - \frac{1}{2}$

Length ft 19 – 65.6, depending on thickness

Width, for $\frac{1}{32}$ to $\frac{1}{8}$ in thickness in 36 Width, for $\frac{3}{16}$ to $\frac{1}{2}$ in thickness in 19

Surface finishingSmoothColorGrey, Black, *White, *Red

*Subject to MOQ

2. PHYSICAL PROPERTIES

Compression deflection (25%)	psi (kPa)	6-14 (41-96)	ASTM D1056
Density	pcf (kg/m ³)	23 (370)	ASTM D1056
Compression set (22h, 100°C)	%	< 1	ASTM D1056
Tensile strength	psi (kPa)	32 (220)	ASTM D412
Elongation	%	80	ASTM D412
Water absorption	%	0.3	ASTM D1056
Flammability	-	V-0 & HF-1 rating	UL-94
Low temperature flexibility	°C (°F)	-55 (-67)	ASTM D1056

Working temperature range °C (°F) -55 to 200 (-67 to 392)

3. INDUSTRY STANDARDS

FDA regulation 21 CFR 77.2600 Rubber articles intended for repeated use

UL-94 V & HBF ≥ 0.8mm thickness

ASTM D1056-14 2D2/3

SAE AMS3195 Rev. H Compliant to physical property requirements

4. TOLERANCES

TARGET THICKNESS, in (mm)	MINIMUM, mm	MAXIMUM, mm
1/32 (0.8)	0.698	1.181
1/16 (1.6)	1.092	2.108
3/32 (2.4)	1.892	2.908
1/8 (3.2)	2.565	3.835
3/16 (4.8)	4.165	5.435
1/4 (6.4)	5.638	7.162
3/8 (9.5)	8.357	10.643
1/2 (12.7)	11.430	13.970

Length tolerance +free / -0 Width tolerance +free / -0