

Name **Extra Soft Grade Silicone Foam**
Code **88-NS200**

1. DIMENSIONS AND APPEARANCE

Thickness	in	1/16 - 1/2
Length	ft	16.4 – 65.6, depending on thickness
Width	in	18
Surface finishing		Smooth
Color		Grey, Black, White*, Red*

*Subject to MOQ

2. PHYSICAL PROPERTIES

Compression deflection (25%)	psi (kPa)	3 (20)	ASTM D1056
Density	pcf (kg/m ³)	17 (270)	ASTM D1056
Compression set (22h, 100°C)	%	< 5	ASTM D1056
Tensile strength	psi (kPa)	22 (150)	ASTM D412
Elongation	%	60	ASTM D412
Flammability	-	V-0 & HF-1 rating	UL-94
Low temperature flexibility	°C (°F)	-55 (-67)	ASTM D1056
Working temperature range	°C (°F)	-55 to 200 (-67 to 392)	

3. INDUSTRY STANDARDS

FDA regulation 21 CFR 177.2600 Rubber articles intended for repeated use
UL-94 V-0 & HBF HF-1 ≥ 0.8mm thickness

4. TOLERANCES

TARGET THICKNESS, in (mm)	MINIMUM, mm	MAXIMUM, mm
1/32 (0.8)	0.698	1.181
1/16 (1.6)	1.092	2.108
3/32 (2.4)	1.892	2.908
1/8 (3.2)	2.565	3.835
3/16 (4.8)	4.165	5.435
1/4 (6.4)	5.638	7.162
3/8 (9.5)	8.357	10.643
1/2 (12.7)	11.430	13.970

Length tolerance +free / -0
Width tolerance +free / -0

GCP Elastomeric Inc. cannot foresee all circumstances under which this information and our products in conjunction with other manufactures products may be used. Physical properties are typical values obtained from sample testing at Akron laboratories or GCP Approved Supplier™ laboratories. Actual production values may vary. It is the users' responsibility to ensure the products are appropriate for their application. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products, either alone or in combination with other products. If you have any questions in this regard please contact our technical director George Qu (george@gcpindustrial.com).